

A high-purity, oxygen-free copper with high electrical conductivity. It is not susceptible to hydrogen disease (embrittlement) when heated in hydrogenous atmosphere.

For industrial applications, oxygen-free copper is valued more for its chemical purity than its electrical conductivity.

This copper is finished to a final form in a carefully regulated, oxygen-free environment and it achieves a minimum 101% IACS conductivity rating. For this reason it is normally more expensive than other grades of copper.

### Chemical Composition (wt. %)

Cu	Minimum 99.95
O	Maximum 0.0010

### Physical Properties

Density	g/cm <sup>3</sup>	8.94
Coefficient of Thermal Expansion	10 <sup>-6</sup> /K	17.7
Electrical Conductivity	MS/m	58
	%IACS	101
Thermal Conductivity	W/(mK)	394
Modulus of Elasticity	kN/mm <sup>2</sup>	127

### Material Designation

Aurubis	-
EN	CW008A
UNS*	C10200
ISO	Cu-OF
BS	C103

\* Unified Numbering System

### Mechanical Properties

		R 220 H 040	R 240 H 065	R 290 H 090	R 360 H 110
Tensile Strength <i>R<sub>m</sub></i>	N/mm <sup>2</sup>	220 – 260	240 – 300	290 – 360	> 360
Yield Strength <i>R<sub>p0.2</sub></i>	N/mm <sup>2</sup>	< 140	> 180	> 250	> 320
Elongation <i>A<sub>50</sub></i>	%	> 33	> 8	> 4	> 2
Hardness <i>H<sub>v</sub></i>	-	40 – 65	65 – 95	90 – 110	> 110

The above mentioned data is general technical product information only and is not a legal warranty. Binding specifications are subject to a later conclusion of contract. This document is not subject to revision. Aurubis UK believes the information contained herein to be reliable. However, technical information is given by Aurubis UK without charge, and the user should employ such information at their own discretion and risk; Aurubis UK assumes no responsibility for results obtained or damages incurred from the use of such information in whole or in part.

## Bendability

	R 220	R 240	R 290	R 360
r = x·t (t ≤ 0.5mm)	90° GW**	0	0	0
	90° BW	0	0	0

\*\* GW: bending edge ⊥ rolling direction, BW: bending edge || rolling direction.

## Fabrication Properties

Cold Formability	Excellent
Hot Formability	Excellent
Soldering	Excellent
Brazing	Excellent
Oxyacetylene Welding	Fair
Gas Shield Arc Welding	Good
Resistance Welding	Poor

## Typical Applications

Electrical Engineering  
Busbars, Super Conductors  
Transistor Components  
Connectors, Coaxial Cables

## Other Properties

Corrosion Resistance	Resistant to corrosion in most atmospheres including marine and industrial environments. Material corroded by oxidising acids, halogens, sulphides and ammonia based solutions.
Work Hardening	Work hardens relatively slowly during cold working and can be annealed in neutral or oxidising atmospheres. Annealing can be achieved by rapid cooling after heating (370°C to 650°C).

The above mentioned data is general technical product information only and is not a legal warranty. Binding specifications are subject to a later conclusion of contract. This document is not subject to revision. Aurubis UK believes the information contained herein to be reliable. However, technical information is given by Aurubis UK without charge, and the user should employ such information at their own discretion and risk; Aurubis UK assumes no responsibility for results obtained or damages incurred from the use of such information in whole or in part.

Aurubis UK Ltd • Rabone Park • Rabone Lane • Smethwick • West Midlands • B66 2NN • United Kingdom

Tel. +44 (0)121 555 1199 • Fax. +44 (0)121 555 1188 • info-uk@aurubis.com • www.aurubis.co.uk